



Exfilm® FP26

High Speed Shrink Film

Standard Dimensions:

Thickness (µm) Exfilm® FP26	Length (m)						Width (mm)	
	Flat				Centerfolded		Flat	Centerfolded
12.5	19.800	9.900	6.600	3.300	3.300	1.650	from 200 up to 1200 width increments of 10mm	from 2 x 150 up to 2 x 1.000 width increments of 50mm
15	16.500	8.250	5.500	2.750	2.750	1.375		
19	12.900	6.450	4.300	2.150	2.150	1.075		
25	9.000	4.500	3.000	1.500	1.500	750		

Cardboard core internal 76mm.

Exfilm® FP26							
Properties		Units	Test Method	Thickness			
				12,5µm	15µm	19µm	25µm
Yield		m ² /kg		87,0	72,5	57,2	43,5
Unit Weight		g/m ²		11,5	13,8	17,5	23,0
Max. Storage Temperature		°C		35			
Heat Shrinkage	MD	%	120°C, air, 5 min	55			
	TD						
Tensile Strength	MD	M P a	ASTM D 882	105	100	100	90
	TD			110	105	105	90
Elongation at Break	MD	%	ASTM D 882	120	120	140	140
	TD			120	130	140	140
Coefficient of Friction			ASTM D 1894	0,25			
Haze		%	ASTM D 1003	2,3	2,8	3,2	3,5
Gloss		%	ASTM D 2457 20°	125	115	110	105

These are nominal values.

SCAN-PACK

ALLE TYPER PAKKEMASKINER
OG EMBALLASJE

SCAN-PACK NORGE A/S
Haugveien 72
2070 Råholt
Norway
Telf: +47 63 95 95 95
Fax: +47 63 95 95 96
E-mail: daniel@scan-pack.no
Web: www.scan-pack.no
Firma reg: NO 866 342 032